

Tenoflex Counters

Thermoplastic counter material – coated on both sides – on non-woven base with excellent shape reproduction and retention.

Types available: **Thickness approx.:**

Tenoflex C 16	0.90 - 1.00 mm
Tenoflex C 26	1.00 - 1.10 mm
Tenoflex C 36	1.10 - 1.20 mm
Tenoflex C 46	1.20 - 1.30 mm
Tenoflex C 56	1.30 - 1.40 mm
Tenoflex C 66	1.45 - 1.60 mm
Tenoflex C 76	1.60 - 1.75 mm
Tenoflex C 86	1.80 - 2.00 mm
Tenoflex C 36 special	1.20 - 1.30 mm
Tenoflex C 46 special	1.30 - 1.40 mm
Tenoflex C 56 special	1.50 - 1.60 mm
Tenoflex C 66 special	1.80 - 1.90 mm

Method for use: Use a Hot / Cold machine to get the best result:
Required interface temperature for bonding: 90 -100°C
Temperature at the hot mould: 130-160°C
Dwell time: 12 - 18 sec.
All data may vary according to substance of material and type of upper.

Delivery: In sheets, 10 sheets piled together and edge trimmed on pallets or as counters – already cut and skived.

Cutting: In length direction as indicated on the sheets.

Skiving: Steel bottom roller and i.e. Fortuna skiving foot 361 HP

Premoulding: Normal versions can be premoulded for easy insertion, »Special« versions are not suitable for premoulding

Sheet size: 1.50 x 1.00m

Manufacturers warranty: Due to the great number of materials being used for shoe manufacturing the possibilities of chemical reactions and incompatibilities between components should be always tested beforehand. We are not liable for damages arising by non observance of our instructions for applications or from reactions beyond our influence and control.

Storing: Under normal conditions the storage is unlimited. Avoid direct storing in the sun. We guarantee for the goods 6 month after delivery date.