

Thermoflex RT C

Thermoplastic firm counter material based on woven-non-woven, with excellent shape reproduction.
Coated with EVA-Adhesive.

Types available:

(Both side bonding)

Thermoflex RT C 16
Thermoflex RT C 36

Thickness:

1.00 - 1.20 mm
1.20 - 1.40 mm

(One side bonding)

Thermoflex RT C 35 plus beige
Thermoflex RT C 45 black

1.15 - 1.35 mm
1.25 - 1.40 mm

Method for use:

“Hot - Cold”

Required interface temperature for bonding: 90 -100°C
Activating temperature: approx. 130 -140°C
Time: approx. 20 - 30 sec.

Advice:

All data may vary according to substance of material and type of upper.

Delivery:

In Sheets, 1.00 x 1.50 m

Cutting:

In length direction, as indicated on the sheets.

Skiving:

We recommend a rippled steel bottom roller and i.e. Fortuna skiving foot 361 HP.

Manufacturers warranty: Due to the great number of materials being used for shoe manufacturing the possibilities of chemical reactions and incompatibilities between components should be always tested beforehand. We are not liable for damages arising by non observance of our instructions for applications or from reactions beyond our influence and control.

Storing: Under normal conditions the storage is unlimited. Avoid direct storing in the sun. We guarantee for the goods 6 month after delivery date.